Alpha Resources, LLC Certificate Of Analysis

AR 631 TITANIUM REFERENCE STANDARD LOT # 1216B

*% OXYGEN

*MEAN = 0.359 *One Sigma Standard Deviation = +/- 0.011 *Expanded Uncertainty = +/- 0.022 (k=2, @ 95% confidence) (n=38) % NITROGEN MEAN = 0.0065 One Sigma Standard Deviation = +/- 0.0009 Expanded Uncertainty = +/- 0.0018 (k=2, @ 95% confidence) (n=38)

Note – No primary NMI or ISO 17034 references of this concentration level were available at the time of certification.

% HYDROGEN MEAN = 0.0017 One Sigma Standard Deviation = +/- 0.0002 Expanded Uncertainty = +/- 0.0004 (k=2, @ 95% confidence) (n=88)

Method of Analysis is ASTM E 1409-13, E 1447-09, ARI 034, and ARI 036 Primary (NMI) Standards used for traceability: NIST SRM 360b BCS CRM 356, 357 BCR CRM 059b, 318 NCS CRM NS57104, NS57102, NS57101 ALPHA -AR586-315D, AR651-1213A, AR637-114C, AR651-316C, AR641-211B, AR647-613B, AR642-515B

The intended use of this reference standard is for the calibration and validation of inert gas fusion, InfraRed (Oxygen), and Thermal Conductivity (Nitrogen, Hydrogen) detection analyzers as described in the above ASTM methods. The mean analytical values were derived by separate data sets showing traceability to the above-mentioned reference standards, and reported in mass fraction. The precision values represent the estimated uncertainty derived from the data sets and may not represent your testing capabilities. Refer to your test method for the expanded method derived uncertainty if needed. When necessary, professional judgment is applied toward consideration of data and statistical information. The statistical analysis and the overall direction and coordination of the analytical measurements leading to certification were performed by K.E. Dyer, Technical Manager, at Alpha Resources.

The material used in production of this reference standard was identified in accordance with ARI 032. The samples for round robin testing were selected in accordance with ARI 014. The above values relate only to the material used to produce this standard. This bottle consists of 10g material in .1g (nominal) pins, and is to be used directly from the bottle without preparation. Multiple pins may be used per test method requirements, with a minimum sample size of 1 pin. This product has an indefinite shelf life. This reference material was produced in accordance to ISO 17034 and ISO Guide 31.

Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event, shall Alpha Resources be liable for incidental or consequential damages. This certificate cannot be reproduced except in full.

This is a Certified Reference Material (working reference standard), and is traceable to the above-mentioned standards. For good laboratory practice, it is recommended that all standards be verified prior to use. These test results are accredited under the Alpha Resources Inc. laboratory's ISO/IEC 17025 and ISO Guide 34 accreditation (RMP) issued by ANSI-ASQ/ANAB. Refer to certificate and scope of accreditation(s) AT-1200 and AR-1920.

Certified July 7, 2017

Kent Der

Kent Dyer, Technical Manager

P.O. Box 199; 3090 Johnson Road, Stevensville, MI 49127 USA Phone (269) 465-5559; Fax (269) 465-3629 www.alpharesources.com Page 1 of 1