

# **Certificate of Analysis**

## AR-2773

## ULTIMATE COAL CRM

LOT# 731123 LID # 731123

### DRIFD BASIS VALUES

				DKILD DASI	3 VALULS				
Proximate Analysis		n=	k=	ASTM	Ultimate Analysis		n=	k=	<b>ASTM</b>
% Ash	7.86 ± 0.19	21	2.1	D3174/D7582	% Carbon	70.18 ± 0.48	8	2.4	D5373
% Volatile Matter	39.29 ± 2.46	21	2.1	D3175/D7582	% Hydrogen	4.19 ± 0.56	8	2.4	D5373
% Fixed Carbon(calculated)	(52.85)			D3172	% Nitrogen	0.98 ± 0.16	8	2.4	D5373
% Sulfur	0.62 ± 0.04	28	2.1	D4239	% Oxygen (calculated)	(16.17)			D3176
Btu/lb	11829 ± 63	8	2.4	D5865					
					Sulfur Forms				
Mineral Analysis				ASTM			ASTM		
% Silica	36.43 ± 4.57	8	2.4	D4326/D6349	% Pyritic	(0.05)	D2492		
% Alumina	15.90 ± 1.90	8	2.4	D4326/D6349	% Organic (calculated)	(0.45)	D2492		
% Titania	1.40 ± 0.18	8	2.4	D4326/D6349	% Sulfate	(0.12)	D2492		
% Ferric Oxide	6.59 ± 0.72	8	2.4	D4326/D6349					
% Calcium Oxide	17.07 ± 1.81	8	2.4	D4326/D6349	Ash Fusion Temperature	Degrees F	Degrees F		
% Magnesium Oxide	3.57 ± 0.49	8	2.4	D4326/D6349	ASTM D1857	Reducing	Oxidizing		
% Potassium Oxide	0.51 ± 0.11	8	2.4	D4326/D6349	Initial deformation	(2133)	(2230)		
% Sodium Oxide	0.66 ± 0.10	8	2,4	D4326/D6349	Softening	(2202)	(2251)		
% Sulfur Trioxide	(15.96)			D4326/D6349	Hemispherical	(2226)	(2269	9)	
% Phosphorus Pentoxide	0.67 ± 0.05	8	2.4	D4326/D6349	Fluid/Final	(2340)	(235	5)	
% Strontium Oxide	(0.32)			D4326/D6349					
% Barium Oxide	0.47 ± 0.04	8	2.4	D4326/D6349	% Chlorine D4208/D6721	(0.0257)			
% Manganese Oxide	(0.02)			D4326/D6349	% Fluorine D3761/D5987	(0.0056)			

REFERENCES USED: Sulfur - NIST SRM 2682c, 1632d, NCS FC28006i, BTU - NIST 39i (Benzoic Acid); Mineral Analysis - NIST 1635a, 1634a; Chlorine - SRM 1635a, 1632d; Fluorine - SRM 1635a, 1632d. () Indicates reference or information only value.

The intended use of this standard is for the verification of various tests by the above-mentioned methods. Typical sample size for analytical testing and minimum size is subject to the test method and instrumentation used. The uncertainty values represent the expanded uncertainty obtained through analytical testing by the mentioned ASTM methods utilizing ANOVA, ISO Guide 35, and the Guide to Uncertainty Measurement. Metrological traceability is to the SI derived units expressed as mass fraction percent, temperature, or BTU/lb. Normal test procedures should be employed when using this standard; this includes using the reproducibility and repeatability factors of the method for establishing analytical uncertainty if needed. When necessary, professional judgment is applied toward consideration of data and statistical information. The statistical analysis and the overall direction and coordination of the analytical measurements leading to certification were performed by K.E. Dyer, Chief Chemist at Alpha Resources.

The material used in production of this standard was identified in accordance with ARI-LAB-603. The samples for round-robin testing were selected in accordance with ARI-LAB-625. The above values relate only to the material used to produce this standard. The analytical samples should be dried or corrected for moisture as per the test method you are using. This bottle contains 50g fine coal powder (-60 mesh). While unable to determine a definite shelf life this reference standard should be reviewed 20 years from the date of certification. Once opened this certificate is valid for two years. Keep sealed tight and store under normal laboratory conditions. This certificate cannot be reproduced except in full. Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Alpha Resources be liable for incidental or consequential damages.

This is a Certified Reference Material (CRM) and is traceable to the above-mentioned references. For good laboratory practice it is recommended that all standards be verified as fit for purpose prior to use. This standard was produced in accordance with ISO 17034 (RMP) accreditation issued by ANSI National Accreditation Board. Refer to certificate and scope of accreditation AR1920.

> **EXPIRATION DATE** THIS CRM IS VALID FOR TWO YEARS FROM THE DATE OF OPENING CERTIFIED January 24, 2024. Kent Dyer - Chief Chemist

3090 Johnson Rd. • Stevensville, MI 49127-0199 • Phone (269) 465-5559 • Fax (269) 465-3629 • alpharesources.com