Value Beyond Measure

Certificate of Analysis

AR-2780 ULTIMATE COAL CRM

LOT # 780320 LID # 780320

DRIED BASIS VALUES

Proximate Analysis		n=	k=	ASTM	Ultimate Analysis		n=	k=	ASTM
% Ash	19.33 ± 0.26	20	2.09	D3174/D7582	% Carbon	65.03 ± 0.71	8	2.36	D5373
% Volatile Matter	30.37 ± 1.02	20	2.09	D3175/D7582	% Hydrogen	4.38 ± 0.16	8	2.36	D5373
% Fixed Carbon(calculated)	(50.30)			D3172	% Nitrogen	1.23 ± 0.14	8	2.36	D5373
% Sulfur	3.04 ± 0.08	28	2.05	D4239	% Oxygen (calculated)	(6.99)			D3176
Btu/lb	11571 ± 38	8	2.36	D5865	MAF/DAF BTU (calculated)	(14343)			D3180
Mineral Analysis		n=	k=	ASTM	Sulfur Forms		ASTM		
% Silica	48.53 ± 4.23	8	2.36	D4326/D6349	% Pyritic	(1.03)	D2492		
% Alumina	24.10 ± 1.57	8	2.36	D4326/D6349	% Organic (calculated)	(1.01)	D2492		
% Titania	1.21 ± 0.09	8	2.36	D4326/D6349	% Sulfate	(1.00)	D2492		
% Ferric Oxide	17.18 ± 1.59	8	2.36	D4326/D6349					
% Calcium Oxide	1.62 ± 0.29	8	2.36	D4326/D6349	Ash Fusion Temperature	Degrees F	Degrees F		
% Magnesium Oxide	0.86 ± 0.06	8	2.36	D4326/D6349	ASTM D1857	Reducing	Oxidizing		
% Potassium Oxide	2.57 ± 0.69	8	2.36	D4326/D6349	Initial deformation	(2103)	(2515)		
% Sodium Oxide	(0.41)		/	D4326/D6349	Softening	(2277)	(2566)	
% Sulfur Trioxide	(1.86)		🔼	D4326/D6349	Hemispherical	(2402)	(2592)		
% Phosphorus Pentoxide	(0.28)		-4	D4326/D6349	Fluid/Final	(2510)	(2642)	
% Strontium Oxide	(0.06)		/	D4326/D6349					
% Barium Oxide	(0.07)	/		D4326/D6349	% Chlorine D4208/D6721	(0.144)			
% Manganese Oxide	(0.04)	/		D4326/D6349	% Fluorine D3761/D5987	(0.0089)			
% Undetermined(calculated)	(1.21)	-4							

REFERENCES USED: Sulfur - NIST SRM 2684c, 2693, FC28012c; BTU - NIST 39j(Benzoic Acid); C/H/N - Phenylalanine, EDTA; Form of Sulfur - QAR-RM-6, LQSI 140022; Mineral Analysis - NIST 634a, 2689, USGS AGV-2; Chlorine - SRM2693, 2682c; Fluorine - 1632d, SARM18.

() Indicates reference or information only value.

The intended use of this standard is for the verification of various tests by the above-mentioned methods. Typical sample size for analytical testing and minimum size is subject to the test method and instrumentation used. The uncertainty values represent the expanded uncertainty obtained through analytical testing by the mentioned ASTM methods utilizing ANOVA, ISO Guide 35, and the Guide to Uncertainty Measurement. Metrological traceability is to the SI derived units expressed as mass fraction percent, temperature, or BTU/lb. Normal test procedures should be employed when using this standard; this includes using the *reproducibility* and *repeatability* factors of the method for establishing analytical uncertainty if needed. When necessary, professional judgment is applied toward consideration of data and statistical information. The statistical analysis and the overall direction and coordination of the analytical measurements leading to certification were performed by K.E. Dyer, Chief Chemist at Alpha Resources.

The material used in production of this standard was identified in accordance with ARI 041. The samples for round-robin testing were selected in accordance with ARI 031. The above values relate only to the material used to produce this standard. The analytical samples should be dried or corrected for moisture as per the test method you are using. This bottle contains 50g fine coal powder (-60 mesh). While unable to determine a definite shelf life this reference standard should be reviewed 20 years from the date of certification. Once opened this certificate is valid for two years. Keep sealed tight and store under normal laboratory conditions. This certificate cannot be reproduced except in full. Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Alpha Resources be liable for incidental or consequential damages.

This is a Certified Reference Material (CRM) and is traceable to the above-mentioned references. For good laboratory practice it is recommended that all standards be verified as fit for purpose prior to use. This standard was produced in accordance to ISO 17034 (RMP) accreditation issued by ANSI-ASQ/ANAB. Refer to certificate and scope of accreditation AR1920.

EXPIRATION DATE
THIS CRM IS VALID FOR TWO YEARS FROM THE DATE OF OPENING
CERTIFIED May 26, 2020