



Certificate of Analysis

AR2780, Lot# 240304

Ultimate Coal CRM

AR2780, Lot# 240304 – Certified Values (Dried Basis)						
Proximate Analysis						
	ASTM Method	Mean	St Dev	Expanded Uncertainty	n	k
% Ash	D3174/D7582	19.18	0.12	0.24	21	2.09
% Volatile Matter	D3175/D7582	29.28	0.75	1.56	21	2.09
% Fixed Carbon (calc)	D3172	(51.16)	--	--	--	--
% Sulfur	D4239	3.31	0.13	0.27	40	2.02
BTU/lb	D5865	11377	33	78	8	2.36
Ultimate Analysis						
	ASTM Method	Mean	St Dev	Expanded Uncertainty	n	k
% Carbon	D5373	64.27	0.31	0.73	8	2.36
% Hydrogen	D5373	4.04	0.26	0.62	8	2.36
% Nitrogen	D5373	1.19	0.12	0.28	8	2.36
% Oxygen (calc)	D3176	(7.98)	--	--	--	--
MAF/DAF BTU (calc)	D3180	(14075)	--	--	--	--
Mineral Analysis						
	ASTM Method	Mean	St Dev	Expanded Uncertainty	n	k
% Silica	D4326/D6349	46.21	0.31	0.73	8	2.36
% Alumina	D4326/D6349	22.80	0.27	0.63	8	2.36
% Titania	D4326/D6349	1.13	0.05	0.13	8	2.36
% Ferric Oxide	D4326/D6349	19.63	0.26	0.63	8	2.36
% Calcium Oxide	D4326/D6349	2.49	0.08	0.20	8	2.36
% Magnesium Oxide	D4326/D6349	1.00	0.04	0.10	8	2.36
% Potassium Oxide	D4326/D6349	2.26	0.17	0.41	8	2.36
% Sodium Oxide	D4326/D6349	(0.32)	--	--	8	2.36
% Sulfur Trioxide	D4326/D6349	(3.35)	--	--	8	2.36
% Phosphorus Pentoxide	D4326/D6349	(0.31)	--	--	8	2.36
% Strontium Oxide	D4326/D6349	(0.07)	--	--	8	2.36
% Barium Oxide	D4326/D6349	(0.10)	--	--	8	2.36
% Manganese Oxide	D4326/D6349	(0.05)	--	--	8	2.36



Additional Values			
Sulfur Forms			
	ASTM Method	Value	
% Pyritic	D2492	(1.34)	
% Organic (calc)	D2492	(0.96)	
% Sulfate	D2492	(1.01)	
Ash Fusion Temperature			
	ASTM Method	Degrees F Reducing	Degrees F Oxidizing
Initial deformation	D1857	(2100)	(2485)
Softening	D1857	(2241)	(2521)
Hemispherical	D1857	(2353)	(2538)
Fluid/Final	D1857	(2422)	(2590)
Halogens			
	ASTM Method	Value	
% Chlorine	D4208/D6721	(0.121)	
% Fluorine	D3761/D5987	(0.0097)	

Note: Parentheses () indicate an information-only value.

Primary (NMI)/GUIDE 34/ISO 17034 Reference Standards Employed:

Test	Primary Reference Standards
% Sulfur	NIST SRM 2684c, 2685c; NCS FC28009F; AR1709-709512, AR1710-710621; QAR CRM-9a; LQSI 8H0158
% C/H/N	EDTA, phenylalanine
Mineral Analysis	USGS AGV-2; NIST 634A, 2691, 16359
BTU	Benzoic acid
Volatile Matter	LQSI 200045
Ash Fusion	LQSI 200049
Halogens	QAR-CRM-3a; NIST 2682c, 2684c, 8499

AR2780 is a Certified Reference Material (CRM) traceable to the above-mentioned reference standards. All reference materials should be verified as fit for purpose prior to use. Analytical values are accredited under Alpha Resources, LLC ISO/IEC 17025 and ISO 17034 accreditation issued by ANSI National Accreditation Board (ANAB). Please refer to certificates and scopes of accreditation AT-1200 and AR-1920. This material is intended to be dried or corrected for moisture as per the test methods used. Each bottle contains 50 g of fine coal powder (-60 mesh). Typical sample size for analytical testing is dependent upon the test method and instrumentation used.

The intended use of this Ultimate Coal CRM is for the verification of various tests using the above-mentioned test methods. The mean analytical values were derived by separate data sets with traceability to the above-mentioned reference standards. Metrological traceability is to the SI derived unit of mass fraction expressed as percent and BTU/lb. The precision values represent the estimated mean value and uncertainty derived from the data sets utilizing ANOVA, ISO Guide 35, and the Guide to Uncertainty Measurement. Refer to the test method for additional information related to measurement uncertainty.

Values are valid for 15 years from the date of certification. Keep sealed tight and store under normal laboratory conditions. This certificate cannot be reproduced except in full. Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Alpha Resources be liable for incidental or consequential damages. Produced in accordance with ISO 17034.

Certification Date: April 19, 2024
Updated: February 14, 2025



Dustin Jenkins, Ph.D.
Global Technical Director

