



Certificate of Analysis

AR 957

RESULFURIZED CARBON STEEL CHIP CRM

LOT # 623A

% CARBON

MEAN = 0.175

Standard Deviation = ± 0.004

Expanded Uncertainty = ± 0.008

(k=2, @ 95% confidence) n=40

% SULFUR

MEAN = 0.108

Standard Deviation = ± 0.002

Expanded Uncertainty = ± 0.005

(k=2, @ 95% confidence) n=40

% NITROGEN

MEAN = 0.0113

Standard Deviation = ± 0.0002

Expanded Uncertainty = ± 0.0006

(k=2, @ 95% confidence) n=40

Method of Analysis is ASTM E 1019-18, ARI-LAB-621 and ARI-LAB-622

Primary (NMI)/GUIDE 34/ISO 17034 Reference Standards Employed:

NIST	343a, 16f, 123c, 8k, 19h, 133b, 335, 50c, 368, 345b
BAM/BCS	183-1, 079-1, 232/2
JSS	604-9, 030-9
NCS	NS11011, HC11007

ALPHA - AR957-421K, AR957-717F, AR957-219E, AR957-1013D, AR957-61709, AR960-512A,
AR951-123D, AR957-914E, AR954-218B, AR1656-214B

The intended use of this reference material standard is for the calibration and verification of Carbon/Sulfur/Nitrogen analysis as described by ASTM E-1019. The mean analytical values were derived by data sets showing traceability to the above-mentioned references. The minimum and typical size used for testing was 1 g. The precision values represent the estimated mean, standard deviation, and expanded uncertainty derived from the data sets using ISO Guide 35, ANOVA, and the Guide to Uncertainty Measurement. Metrological traceability is to the SI derived unit of mass fraction expressed as percent. Refer to your test method for additional uncertainty information. When necessary, professional judgment is applied toward consideration of data and statistical information. The statistical analysis and the overall direction and coordination of the analytical measurements leading to certification were performed by **Dustin Jenkins Ph.D.**, Global Technical Director at Alpha Resources.

The material used in production of this reference material standard was identified in accordance with ARI-LAB-604. The samples for round robin testing were selected in accordance with ARI-LAB-625. The above values relate only to the material used to produce this product. This bottle contains 150g steel chips, to be used directly from the bottle with no preparation needed. While unable to determine a definite shelf life, this reference should be reviewed every 25 years from the date of certification. Keep sealed and store under normal laboratory conditions. Remedies for any claimed defect in this product will be limited to product replacement or refund of the purchase price. In no event shall Alpha Resources be liable for incidental or consequential damages. This certificate cannot be reproduced except in full.

This is a Certified Reference Material (CRM) and is traceable to the above-mentioned reference materials. For good laboratory practice, it is recommended that all references be verified as fit for purpose prior to use. These test results are accredited by Alpha Resources LLC. laboratory's ISO/IEC 17025 and ISO 17034 accreditation (RMP) issued by ANSI National Accreditation Board. Refer to certificate and scope of accreditation(s) AT-1200 and AR-1920.

Certified: 2024/04/04
Dustin Jenkins, Ph.D.
Global Technical Director